

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
9 October 2003 (09.10.2003)

PCT

(10) International Publication Number  
**WO 03/082500 A1**

(51) International Patent Classification<sup>7</sup>: **B22D 41/54**

ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(21) International Application Number: PCT/BE03/00056

(22) International Filing Date: 28 March 2003 (28.03.2003)

**Declarations under Rule 4.17:**

(25) Filing Language: English

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

(26) Publication Language: English

(30) Priority Data:  
02447051.0 29 March 2002 (29.03.2002) EP

(71) Applicant (for all designated States except US): **VESUVIUS CRUCIBLE COMPANY** [US/US]; Suite 200, 103 Foulk Road, Wilmington, DE 19803 (US).

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— of inventorship (Rule 4.17(iv)) for US only

(72) Inventors; and

(75) Inventors/Applicants (for US only): **HANSE, Eric** [BE/FR]; 17, rue Henri Bosselin, F-59750 Feignies (FR). **DELVOYE, François** [FR/FR]; 211 Avenue Jean Jaurès, F- 59600 Maubeuge (FR). **LAVIE, Philippe** [FR/FR]; 24 Rue du Bon Dieu Cauwere, B-5032 Bossière (FR).

(74) Agent: **DEBLED, Thierry**; Vesuvius Group S.A., Intellectual Property Department, Rue de Douvrain 17, B-7011 Ghlin (BE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

**Published:**

— with international search report

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: THERMAL SHOCK RESISTANT CASTING ELEMENT AND MANUFACTURING PROCESS THEREOF

(57) Abstract: The present invention concerns an element for the casting of a liquid metal, comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal. This element is characterized in that at least a part of the element inner surface is coated with an insulating coating forming, at the metal liquid contact, a gas impermeable layer. Such an element has an excellent thermal shock resistance which permits its use without preheating. Then a layer reducing advantageously the gas permeability is formed.



WO 03/082500 A1

**Thermal shock resistant casting element and manufacturing process thereof.****Specification.**

[0001] The present invention relates to a refractory element used for the transfer of molten metal. A particular case wherein the invention is very advantageous is a refractory tube for the transfer of steel from a ladle to a tundish and particularly such a tube when used without preheating.

5 [0002] Refractory elements used in molten metal casting are by nature, extremely sensitive to thermal shocks. When they are used, the elements contact metal and are subjected to important thermal shocks generating the formation of cracks, and this all the more when the temperature is low before their use. Consequently, the life time of these elements is reduced. Moreover, the cracks can permit air entries which can lead to downgrading the cast metal quality.

10 [0003] In order to improve the thermal shock resistance of the elements, a widely spread technique consists in preheating the element to temperature as close as possible to the use temperature. However, this technique requires to have a preheating zone near the use zone of the elements, consumes energy and consequently is expensive. Further, there is a minimum preheating time before which the element is not enough preheated to resist a thermal shock and a maximum preheating time beyond which the element starts to deteriorate. This process lacks also some flexibility since it does not allow to face an unexpected event, or too important deviation with respect to manufacturing planning.

15 [0004] Another technique well known by the skilled in the art and combined with that above described is the use of insulating fibers which are either glued, either cemented on the outside of the refractory element. In this case, the external coating permits to keep longer the heat acquired during the preheating and to increase its efficiency. However, the fibers which can support high temperatures ( $> 1000^{\circ}\text{C}$ ) necessary in these applications are toxic and their use is less and less authorized.

20 [0005] Document DE 38 05 334 A1 discloses another method permitting to improve the thermal shock resistance of such elements. This method consists in introducing in the pouring orifice of the element a sleeve made from a fibrous or foaming ceramic material. This method has several drawbacks. When a foaming ceramic material is used, to form it, it is necessary to use foaming or tensioactive -agents which are generally incompatible with refractory elements, particularly if they are constituted from carbon bonded material. It can also be difficult to control the foam so as to form a layer of relatively constant thickness and showing reproducible insulating properties. The so obtained insulation is thus not homogenous and can cause detrimental temperature gradients inside the element. When the element has a complex geometry, which is more and more frequent to improve the cast metal quality, the manufacturing and the positioning of the sleeve is specially uneasy, in particular to ensure a continuous contact between the sleeve and the element. As the sleeve is not integral with the element, it can move or even come off during the handling or usage of the element when contacting the metal. Parts of the sleeve can

25  
30  
35

obstruct the element, form a plug or, at least, make uneasy the passage of molten metal since the metal cannot flow normally in the lower metallurgical vessel; it can then leak through the joints bonding the refractory elements to one another.

5 [0006] In the particular case of refractory pouring tube, intended for the transfer of a molten metal from a casting ladle to a tundish, these being generally tubes made from graphite based materials and carbon bonded (alumina/graphite, magnesia/graphite, ...), the most often used method is certainly the one consisting in pre-oxidizing the inner surface of the tube so as to form a layer without or with only a reduced carbon percentage. This low carbon content oxidized layer is a layer that shows a low thermal conductivity coefficient with respect to the body of the  
10 tube. It acts as a barrier at the beginning of the casting and permits to the refractory tube to resist the thermal shock of the first contact with the molten metal.

This method, although generally satisfactory, has nevertheless some drawbacks. The oxidized layer is obtained during the firing of the refractory tube under oxidizing atmosphere. It is therefore quite uneasy to obtain an homogenous layer of constant thickness all along the  
15 element. The thickness of the oxidized layer can vary significantly (2 to 10 mm) from one tube to another or from one region to another of the same tube. This does not permit to have homogenous insulating properties. Further, this layer having lost its carbon binder is washed away in a few minutes at the contact of the molten metal. The thickness of the tube is therefore quickly reduced of the thickness of the layer; this reduces significantly the mechanical resistance  
20 and its time life.

[0007] The object of the present invention is a casting element having an increased thermal shock resistance and which does not have the drawbacks of the above mentioned prior art. Moreover, it would be desirable to propose a refractory element having improved properties, particularly a gas permeability significantly reduced with respect to the element of the state of the  
25 art.

[0008] The casting element according to the invention comprises a base body made from a refractory material. This base body comprises an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal.

[0009] The present invention is based on the observation that the thermal shock resistance  
30 properties are essentially useful at the beginning of the use of the non preheated element. It is indeed necessary that such an element can resist important thermal shock (passage from the room temperature to the molten metal temperature) in a very short time (a few seconds). Later, the element being used at its regime temperature, it is not any longer subjected to so important temperature variations and its thermal shock resistance becomes less crucial. It is to be noted  
35 that a temporary stop of the casting operation (for example when the casting ladle is changed) does not allow a cooling of the element beyond a critical point and does not lead to important thermal shock. On the other hand, once the temperature regime reached, it would be desirable to take into account other quality factors of the casting elements such as the non-permeability to gas. In particular, it would be highly desirable to ensure a good thermal shock resistance of the

element at the beginning of its use (cold start) and a good gas impermeability during the continuation of its use.

**[0010]** The casting element according to the invention is characterized in that at least a part of the element inner surface is coated with an insulating coating forming, at the metal liquid contact, a gas impermeable layer. The insulating coating covering the cold element permits to the element to resist the thermal shock at the start of its use, i.e. when the liquid metal contacts the inner part of the element. The impermeable layer formed at the contact with the liquid metal provides gas impermeability to the element, the air entries will therefore be reduced or even eliminated and the cast metal quality improved. Generally, such an impermeable layer is generated after from a few seconds to a few minutes.

**[0011]** The coating comprises components providing for its insulating properties as well as components that will promote the formation of an impermeable layer at the contact with the liquid metal. It must be noted that the same component can play both roles. The components of the coating providing for the insulating properties are for example insulating microspheres. The coating components able to form an impermeable layer at the casting temperatures are for example silica and alumina.

**[0012]** According to an embodiment of the invention, the coating comprises from 20 to 80% by weight of a ceramic matrix, 5 to 40 % by weight of insulating microspheres, from 0.5 to 15 % by weight of one or more binders, and up to 5 % of water. The coating can also comprise 5 to 20 % by weight of a metal or a metallic alloy so as to improve the continuity of the coating and, consequently, the texture of the coating. According to a particular case, the ceramic matrix comprises silica or alumina, for example, vitreous grains such a atomized silica. Atomized silica being extremely fine, it has the advantage of easily penetrating inside the porosity of the element body and, therefore, bond the coating and the body material. Insulating microspheres comprise also, for example, silica and/or alumina.

**[0013]** Some of the components of the coating forming the gas impermeable layer can react with some components contained in the liquid metal as well as with some components contained in the casting element body material. The result of these reactions are low melting point phases, molten or vitreous at use temperature which cover and make impermeable the surface of the element. It has been noted that, advantageously, these phases show a relatively high viscosity permitting an excellent bonding to the inner surface of the element. In particular, these phases are not damaged during the first cleanings of the element, for example with oxygen. It has been noted that these reactions take place even when these components are present in a very low amount. The components of the metal suitable to participate to these reactions are for example calcium, magnesium or manganese. The components of the element body material are for example magnesia and mullite.

**[0014]** In a particular embodiment, the casting element is a ladle shroud, for example in a carbon bonded refractory material not pre-heated before its use.

**[0015]** The thickness of the coating can vary from 1 to 10 mm, good results have been obtained

with a thickness of from 3 to 5 mm.

**[0016]** The insulating coating is applied on a part of the inner surface of the casting element. According to an embodiment of the invention, the coating shows a structure and a grain size distribution such that the coating and the material forming the body of the casting element are

5 bonded one to the other, the coating penetrating into the porosity of the material, for example by wetting or capillary action. There is thus an inter-penetration of the body material and the coating which become integral.

**[0017]** The element coating will turn, in use, into an impermeable layer which will remain integral with the casting element body material.

10 **[0018]** In order to improve the thermal shock resistance, several layers of the coating can be necessary, for example for hard applications.

**[0019]** A layer of an insulating coating similar or different of the one according to the invention can also be applied on a part of the external surface of the casting element, for example on a part of the external surface of the element likely to be immersed into the liquid metal. This part  
15 must indeed resist the inner thermal shock during the first passage of the liquid metal as well as the thermal shock at the immersion into the liquid metal.

**[0020]** The present invention relates also to a process for coating a casting element characterized in that at least a part of the element inner surface is coated with an insulating coating forming, at the metal liquid contact, a gas impermeable layer, said casting element  
20 comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a channel.

**[0021]** The coating can be applied on the tube surface by spraying, brushing or even by dipping into an aqueous solution or a slip. It is also possible to simply pour an aqueous solution or slip through the channel defined by the inner surface of the element. In the scope of the present  
25 invention, it is meant by slip a suspension in water or in another liquid of fine particles (with a dimension lower than 50  $\mu\text{m}$ ) or of such a suspension comprising further coarse particles (with grains having a dimension of up to 2 mm).

**[0022]** The inter-penetration of the coating and the element body material is promoted when the coating is prepared as an aqueous solution or a slip, applied to the element and then dried, for  
30 example in the open air. A coating which have provided excellent results is a coating comprising 20 to 80 weight % atomized silica with respect to the total weight of the coating. The atomized silica is indeed easily converted into a slip and penetrates easily into the element body material porosity.

**[0023]** In an embodiment of the invention, a coating comprising 20 to weight 80 % of a ceramic  
35 matrix, 5 to 40 weight % of insulating microspheres, from 0.5 to 15 weight % of one or more binders and up to 5 % of water is prepared as a slip, said slip is contacted with the surface of the element to be coated and is then dried for at least two hours.

**[0024]** The coating can also comprise from 5 to 20 % by weight of a metal or metal alloy so as to improve the coating process of the element and reduce the formation of cracks during the

drying.

**[0025]** Example

**[0026]** A carbon bonded pouring shroud constituted from alumina graphite, the inner surface of which has not been oxidized is used. A coating comprising :

- 5           12.1 % water
- 2.9 % dextrin
- 7.8 % colloidal silica
- 1.7 % dolapix CE 64

(dolapix CE 64 is a defloculating agent from the German company ZCHIMMER &

10   SCHWARZ AG.)

- 8.6 % fillite
- 4.1 % clay
- 42.9 % atomized silica
- 10.7 % alumina
- 15       9.1 % aluminum (metal)
- 0.1 % sodium tripolyphosphate

is prepared under the form of a slip. The end of the tube is plugged with a rubber tab. The inside of the tube is filled with the slip. After from 20 to 30 seconds, the end of the tube is open and the slip in excess is evacuated. The inner surface of the tube is thus coated with a coating  
20   layer having an essentially constant thickness. The coating and the tube material being interconnected. The element is then dried in open air for about two hours.

**[0027]** An element prepared according to the example has been compared to a known element comprising a 5 mm oxidized layer on its inner surface. After use, the element according to the invention showed no cracks and its time life was much longer than this of the state of the art  
25   element.

**[0028]** The inner surface of the element according to the invention was covered with a layer having a vitreous appearance and gas impermeable. This molten layer comprised, among other, calcia aluminates, calcia silico-aluminates and manganese silicate.

**[0029]** For certain critical applications where a preheating would still be required, the coating  
30   according to the present invention is able to resist such a preheating.

**Claims.**

1. Element for the casting of a liquid metal, comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal, **characterized in that** at least a part of the element inner surface is coated with an insulating coating forming, at the metal liquid contact, a gas impermeable layer.
2. Casting element according to claim 1, **characterized in that** the coating comprises 20 to 80 weight % of a ceramic matrix, preferably comprising silica or alumina.
3. Casting element according to claim 2, **characterized in that** the ceramic matrix comprises vitreous grains, such a atomized silica.
4. Casting element according to any one of claims 1 à 3, **characterized in that** the coating comprises insulating microspheres, preferably in an amount comprised between 5 and 40 weight %.
5. Casting element according to any one of claims 1 à 4, **characterized in that** the thickness of the coating is comprised between 1 and 10 mm.
6. Casting element according to any one of claims 1 à 5, **characterized in that** the impermeable layer and the refractory material are interpenetrated.
7. Casting element according to any one of claims 1 à 6, **characterized in that** the base body is constituted from a carbon bonded material.
8. Casting element according to any one of claims 1 à 7, **characterized in that** the casting element is a pouring shroud.
9. Casting element according to any one of claims 1 à 8, **characterized in that** at least a part of the external surface is coated with an insulating coating.
10. Process for coating a casting element comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal, **characterized in that** at least a part of the element inner surface is coated with an insulating coating forming, at the metal liquid contact, a gas impermeable layer.
11. Process according to claim 10, **characterized in that** the coating is prepared as a slip, the element is contacted with the slip and is dried for at least two hours.

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/BE 03/00056

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 B22D41/54

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B22D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR 2 721 241 A (VESUVIUS FRANCE SA) 22 December 1995 (1995-12-22) claims 1-15; figures 1-5 ---	1-11
A	US 4 498 661 A (KOBZAR VLADIMIR E) 12 February 1985 (1985-02-12) column 3, line 11 -column 5, line 9; figures 1-5 ---	1
A	US 2 063 377 A (GOVERT HELMER) 8 December 1936 (1936-12-08) the whole document ---	1
A	US 5 681 499 A (HANSE ERIC ET AL) 28 October 1997 (1997-10-28) column 9, line 5 - line 31; figures 1,2 -----	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

3 July 2003

Date of mailing of the international search report

10/07/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Mailliard, A



# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No

PCT/BE 03/00056

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
FR 2721241	A	22-12-1995	FR 2721241 A1	22-12-1995
			AT 169535 T	15-08-1998
			AU 697401 B2	08-10-1998
			AU 2795995 A	05-01-1996
			BR 9506265 A	12-08-1997
			CA 2169472 A1	21-12-1995
			CN 1129413 A , B	21-08-1996
			CZ 9600428 A3	11-09-1996
			DE 69504027 D1	17-09-1998
			DE 69504027 T2	01-04-1999
			EP 0721388 A1	17-07-1996
			ES 2122636 T3	16-12-1998
			WO 9534395 A1	21-12-1995
			JP 9503445 T	08-04-1997
			RU 2146186 C1	10-03-2000
			US 5691061 A	25-11-1997
<hr/>				
US 4498661	A	12-02-1985	AU 8902382 A	04-11-1982
			DE 3241331 A1	05-05-1983
			DE 3241331 T0	05-05-1983
			JP 58500798 T	19-05-1983
			SE 8207354 A	22-12-1982
			WO 8203582 A1	28-10-1982
<hr/>				
US 2063377	A	08-12-1936	DE 638612 C	19-11-1936
			FR 787689 A	26-09-1935
			GB 434520 A	03-09-1935
<hr/>				
US 5681499	A	28-10-1997	NONE	
<hr/>				